DIE EAST COAST

DIK EAST COAST

DIK EAST COAST

### 1. Description

DIE EAST COAST

Bisphenol A type liquid epoxy resin E-44 is an unmodified liquid epoxy resin with medium viscosity produced from bisphenol-A and epichlorohydrin. It's viscosity is lower than E-51 and hence is preferred over E-51 where lower DIK EAST COA viscosity plays important role in processing and application. A wide variety of curing agents are available to cure this liquid epoxy resin at ambient conditions and also at elevated temperature. When cured with appropriate hardener, E-44 gives excellent mechanical, chemical, electrical and adhesion properties. Because of these properties it finds use in various applications

## 2. Application

- Solvent based, high solid content and solvent-free coatings
- Adhesives
- Civil and construction engineering industry
- Automotive coatings
- Can & con comme
  Marine and industrial protective coatings
  - Tooling, potting, casting and molding compounds
  - Composites

DIE EAST

#### 3. Product parameters

| Appearance          | Visual         | Transparent, colorless to light yellow liquid |
|---------------------|----------------|---|
| Color               | ASTM D 1544-04 | 0.5Gmax                                       |
| Epoxy equivalent    | ASTM D 1652-04 | 210-188                                       |
| Viscosity (25 )     | ASTM D 2196-05 | 8000-11000cP                                  |
| Hydrolyzed chlorine | ASTM D 1726-03 | 0.05 max                                      |
| Epoxy value         | ASTM D 1652-04 | 5.32-5.55                                     |

# DK FAST COATSU

| Density (25 ) | ASTM D 1475-98 | 1.16g/ml  |
|---------------|----------------|-----------|
| Water content | ASTM E 203-01  | 0.05 max  |
| ECH content   | TEC-AS-P-023   | 10ppm max |
| Flash point   | ASTM D 93      | 150       |

## 4. Product packaging

This product is packed and transported in 220kg sealed iron drum.

Other packaging can be provided on request.

## 5. Storage and precautions

- 1). Epoxy resin should be stored in a cool and dry place, avoid rain and sun exposure.
- 2). When deploying epoxy resin, it is necessary to use it now and mix the curing agent in proper proportion to avoid waste.
- 3). Epoxy resin storage life is generally 1 year, beyond the time limit should be tested, meet the index can still be used.

### Disclaimer

All recommendations for use of our products whether given by us in writing, verbally or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Although, the information contained in this sheet is accurate, no liability can be accepted in respect of such